

On the *ab initio* calculations within DFT + U approach of physical properties of a compound with strong electron-electron correlations by the case of KFeS_2

A. G. Kiiamov¹⁾, M. D. Kuznetsov, R. G. Batulin, D. A. Tayurskii

Department of General Physics, Institute of Physics, Kazan Federal University, 420008 Kazan, Russia

Submitted 24 November 2021
Resubmitted 25 November 2021
Accepted 29 November 2021

DOI: 10.31857/S1234567822020070

A ternary potassium-iron sulfide, KFeS_2 , belongs to a family of quasi-one-dimensional compounds with the general chemical composition AFeCh_2 (where $\text{A} = \text{K}$ or Rb ; $\text{Ch} = \text{S}$ or Se) [1]. Nevertheless, so far, no consensus has been reached on the magnetic ground state of this compound. The correctness of an anticipated Spin-Hamiltonian and corresponding approximations to describe a certain magnetic sub-system of a compound can be checked by comparing the experimental magnetic specific-heat data with the theoretical predictions derived from the model [2]. The magnetic specific heat of a compound can be obtained as a difference between total specific heat and all the other contributions exclude the magnetic one [3].

One way to obtain the lattice specific heat is based on *ab initio* calculations. Density functional theory (DFT) calculations allow to obtain all the phonon modes of a crystal, while the lattice specific heat could be calculated from phonon density of states within the quasi-harmonic approximation [4, 5].

Nevertheless, in the case of a compound with strong electron-electron correlations, like KFeS_2 [6], approaches based on DFT calculations are not well applicable.

DFT + U approach greatly improves the description of materials with mixed type of electron distribution. This materials class includes mid-to-late first row transition metal oxides and sulfides, because the self-interaction error is largest for such multiply charged (i.e., +2 or higher) open-shell metal ions [7]. In the case of magnetically ordered compounds right choice of the U_{eff} parameter is necessary for the correct description of magnetic ground state and magnetic moments value [8]. The magnetic ground state and magnetic moment values of iron ions are well known from neutron diffraction measurements, below Neel tempera-

ture of 250 K [6] KFeS_2 is an antiferromagnet with the magnetic moments value $1.9 \mu_B$ [1].

We have performed the series of *ab initio* calculations of the magnetic and electronic properties of KFeS_2 for the different U_{eff} parameter values. The *ab initio* calculations were based on DFT [9]. As a first approximation the calculations were performed implementing simplified LSDA + U approach [10] with a single parameter $U_{\text{eff}} = U - J$ (the difference between Coulomb and exchange energies [11]).

The conformity between the calculated magnetic moment value and experimentally measured one were obtained for the negative parameter value U_{eff} ($U < J$) of -2 eV .

The correct description of magnetic properties of KFeS_2 within DFT + U approach with U_{eff} parameter value of -2 eV allows to assume that this model can be used for the correct prediction of all physical properties of the compound. Nevertheless, the predicted by the model electronic properties of KFeS_2 are in conflict with available experimental data [12].

Therefore, to obtain the agreement of *ab initio* and experimental results on both electronic and magnetic properties we have performed another series of calculations within the rotationally invariant LSDA + U approach proposed in [13]. On site Coulomb terms U and J have been considered independently for the strong correlated Fe d -electrons.

In a low temperature range $T < T_N \approx 250 \text{ K}$, electrical resistivity of KFeS_2 exhibits exponential increasing [12]. Thus we used the intrinsic semiconductor model in order to describe experimental dependency. The best agreement have been obtained for the band gap value of $E_g \approx 0.35 \text{ eV}$.

The dependency of calculated within DFT + U approach magnetic moment value on iron ions in KFeS_2 on chosen U and J parameters is presented on Fig. 1. The calculated magnetic moment value on iron ions in KFeS_2

¹⁾e-mail: AiratPhD@gmail.com




Fig. 1. (Color online) The calculated magnetic moment value on iron ions in KFeS₂ obtained for different values of U and J parameters

matches with experimental one ($1.9 \mu_B$ [1]) for the set of U and J parameters. The calculations give the correct value of magnetic moment for parameter J of approximately 2 eV and U in the range at least of 1.0–1.5 eV. So, in the case of calibration of U and J parameters by the correctness of magnetic moment values the particular pair of correct parameter values can not be proposed. The calculations within DFT + U approach with different combinations of U and J parameters can reproduce correct magnetic ground state and magnetic moment value while the predicted electronic properties are not in agreement with real properties. Finally, within the rotationally invariant DFT + U approach with $U = 1.5$ eV and $J = 2$ eV parameters, the magnetic and electronic properties of KFeS₂ are described correctly.

To summarize, the magnetic and electronic properties of iron chalcogenide compound KFeS₂ have been calculated within two DFT + U approaches based on (i) simplified LSDA + U approach [10] with a single parameter $U_{\text{eff}} = U - J$ (the difference between Coulomb and exchange energies [11]) and (ii) rotationally invariant LSDA + U approach proposed in [13]. The first model with parameter $U_{\text{eff}} = -2$ eV correctly describes magnetic ground state and magnetic moment value of the compound but incorrectly predicts the compound to be a metal, while below Neel temperature KFeS₂ is a semiconductor with band gap value 0.35 eV. The second approach with the pair of values of the parameters of $U = 1.5$ eV and $J = 2$ eV simultaneously give correct description of magnetic and electronic properties. The correct values of band gap and magnetic moment on iron ions have been obtained. Mentioned above U and J parameters values can be proposed for the cor-

rect description of physical properties of KFeS₂ within DFT + U approach.

This work was supported by the joint RFBR-DFG (Russian Foundation for Basic Research – Deutsche Forschungsgemeinschaft (German Research Foundation)) project #19-52-12068 (RFBR) and #KR 2254/3-1 (DFG).

We thank Dr. Yury Lysogorskiy for fruitful and stimulated discussions.

This is an excerpt of the article “On the *ab initio* calculations within DFT + U approach of physical properties of a compound with strong electron-electron correlations by the case of KFeS₂”. Full text of the paper is published in JETP Letters journal. DOI: 10.1134/S0021364022020023

1. W. Bronger, A. Kyas, and P. Müller, J. Solid State Chem. **70**, 262 (1987).
2. Y. V. Lysogorskiy, R. M. Eremina, T. P. Gavrilova, O. V. Nedopekin, and D. A. Tayurskii, JETP Lett. **100**, 652 (2015).
3. S. M. Stishov and A. E. Petrova, JETP Lett. **114**(5), 318 (2021).
4. A. G. Kiiamov, Y. V. Lysogorskiy, F. G. Vagizov, L. R. Tagirov, D. A. Tayurskii, Z. Seidov, H.-A. Krug von Nidda, V. Tsurkan, D. Croitori, A. Gunther, F. Mayr, and A. Loidl, Phys. Rev. B **98**, 214411 (2018).
5. A. Kiiamov, V. Tsurkan, D. Croitori, H.-A. Krug von Nidda, Z. Seidov, H.-C. Wille, I. Sergueev, O. Lepold, D. Tayurskii, and L. Tagirov, Appl. Sci. **10**(20), 7212 (2020).
6. Z. Seidov, H.-A. Krug von Nidda, V. Tsurkan, I. G. Filippova, A. Gunther, T. P. Gavrilova, F. G. Vagizov, A. G. Kiiamov, L. R. Tagirov, and A. Loidl, Phys. Rev. B. **94**, 134414 (2016).
7. Z. Bendeddouche, A. Zaoui, S. Kacimi, S. Abbaoui, A. Kadiri, and A. Boukortt, JETP Lett. **111**(4), 210 (2020).
8. A. Rohrbach, J. Hafner, and G. Kresse, J. Phys.: Condens. Matter **15**, 979 (2003).
9. P. Hohenberg and W. Kohn, Phys. Rev. **136**, B864 (1964).
10. S. L. Dudarev, G. A. Botton, S. Y. Savrasov, C. J. Humphreys, and A. P. Sutton, Phys. Rev. B **54**, 3 (1998).
11. E. A. Carter, Science **321**, 5890 (2008).
12. S. Nishioka, H. Kuriyaki, and K. Hirakawa, Synth. Met. **71**, 1877 (1995).
13. V. I. Anisimov, F. Aryasetiawan, and A. I. Lichtenstein, J. Phys. Condens. Matter **9**, 4 (1997).